

WINDOW FILM PERFORMANCE DATA | Architectural: Asia Pacific



Solar Control Window Film

	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorptance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter U-value	Shading Coefficient	% Ultraviolet Ray Protection (wavelengths 280-380nm)	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Rejected	Light-to-Solar Heat Gain Ratio (LSG)	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Clear Glass	83	8	9	90	8	8	1.03	1.00	29	0.84	0.86	14	1.05	0	0	0
Reflective Series																
Reflective films feature reflectance on both interiors and exteriors for superior reduction in summer cooling costs and heat retention in winter. Providing a high level of glare and heat control, they are scratch-resistant, shield 99% of ultraviolet rays, and provide excellent heat rejection.																
RN-07G SR CDF (One-Way Mirror)	6	53	41	5	60	14	0.91	0.2	99	0.59	0.16	84	0.31	80	12	94
R-15G SR CDF (Gray)	9	33	58	7	13	61	0.94	0.29	99	0.7	0.25	75	0.28	71	9	92
R-20 SR CDF (Silver)	12	54	34	16	62	62	0.94	0.25	99	0.71	0.21	79	0.76	75	9	82
R-35 SR CDF (Silver)	21	43	36	28	46	49	0.96	0.4	99	0.73	0.31	69	0.9	60	7	69
R-50 SR CDF (Silver)	36	29	35	48	28	26	0.97	0.54	99	0.75	0.46	54	1.04	46	6	47
Dual-Reflective Series																
Dual-Reflective films are highly reflective on the exterior; lower on the interior, which helps provide clear day and night views. Traditionally specified on commercial buildings, Dual-Reflective films are also popular for sunbelt residential applications. They are scratch-resistant, shield 99% of ultraviolet rays, and provide excellent heat rejection.																
DR-15 SR CDF (Warm Gray)	16	37	47	15	37	13	0.92	0.3	99	0.63	0.26	74	0.58	70	11	83
DR-25 SR CDF (Warm Gray)	25	26	49	22	27	13	0.92	0.41	99	0.61	0.35	65	0.63	59	11	76
DR-35 SR CDF (Warm Gray)	35	19	46	36	19	13	0.93	0.52	99	0.61	0.44	56	0.82	48	10	60
Low-E																
Low-E film provides superior energy conservation by reducing winter heat loss through windows. It is scratch-resistant, shields 99% of ultraviolet rays, reduces glare, and has the highest heat rejection performance of all LLumar films. It is suitable for commercial and residential applications where summer and winter energy control are major concerns.																
E-1220 SR CDF (Silver)	8	58	34	12	66	70	0.77	0.18	99	0.36	0.15	85	0.8	82	25	87
LE-AL35 SR CDF (Silver)	18	49	33	28	47	36	0.76	0.28	99.9	0.33	0.24	76	1.17	68	26	69
Deluxe Series																
Deluxe films are specified for commercial buildings where high levels of heat rejection and glare reduction are needed. Deluxe films are ideal for privacy applications and exterior aesthetics. They are scratch-resistant, reduce 99% of ultraviolet rays, and come in gray and bronze.																
DL-05G SR CDF (Gray)	14	25	61	6	13	13	0.92	0.35	99	0.62	0.3	70	0.2	65	11	93
DL-15B SR CDF (Bronze)	27	13	60	14	8	8	0.98	0.45	99	0.77	0.39	61	0.36	55	5	84
DL-15G SR CDF (Gray)	26	15	59	16	9	10	0.99	0.45	99	0.78	0.42	58	0.38	55	4	82
DL-30GN SR CDF (Green)	29	20	51	30	17	17	0.98	0.53	99	0.76	0.46	54	0.65	47	5	67
Neutral Series																
Neutral films reduce glare, provide moderate heat rejection, and are specified where a soft, neutral appearance is desired. These films are made with sputtered technology, creating a film that allows for very uniform visible light transmission. Neutral films are scratch-resistant and shield 99% of ultraviolet rays.																
N-1020 SR CDF (Neutral)	21	26	53	24	29	28	1.03	0.44	99	0.84	0.37	63	0.65	56	0	73
N-1040 SR CDF (Neutral)	36	16	48	40	18	15	1	0.59	99	0.81	0.5	50	0.8	41	3	56
N-1050 SR CDF (Neutral)	44	13	43	49	14	12	1.03	0.67	99	0.84	0.58	42	0.84	33	0	46
N-1065 SR CDF (Neutral)	65	9	26	67	10	9	1.03	0.82	99	0.84	0.71	29	0.94	18	0	26
N-1020B SR CDF (Bronze)	12	49	39	20	37	35	0.93	0.27	99	0.69	0.23	77	0.87	73	10	78
N-1035B SR CDF (Bronze)	25	37	38	37	25	23	0.94	0.41	99	0.71	0.36	64	1.03	59	9	59
Exterior Series																
Exterior Series products are applied to the exterior face of the glazing and provide excellent heat rejection performance.																
NHE-20 ER HPR (Exterior Neutral)	22	23	55	25	24	27	1.04	0.45	99.9	0.84	0.38	62	0.66	55	-1	72
NHE-35 ER HPR (Exterior Neutral)	33	18	49	38	15	19	1.04	0.56	99.9	0.83	0.48	52	0.79	44	-1	58
REX-20 SI ER HPR (Exterior -----)																
RHE-20 ER HPR (Exterior Silver)	10	65	25	14	61	65	1.04	0.20	99.9	0.70	0.17	83	0.82	80	-1	84
RHE-35 ER HPR (Exterior Silver)	18	54	28	25	48	52	1.04	0.30	99.9	0.68	0.26	74	0.96	70	-1	72
RHE-50 ER HPR (Exterior Silver)	33	34	33	45	28	30	1.04	0.50	99.9	0.69	0.43	57	1.05	50	-1	50
THE-80 BL ER HPR (Exterior -----)																
Specialty Series																
AU-85UV SR HPR is the ideal solution for protecting valuables from sun damage. It provides the highest protection against harmful ultraviolet rays without altering glass aesthetics. AIR-80BL SR HPR is used where a combination of extremely low visible reflectance, high light transmission, and substantial reduction in solar infrared transmission is needed.																
AIR-80BL SR HPR (Clear)	48	7	45	79	9	9	0.99	0.71	99	0.75	0.61	39	1.30	29	4	12
AU-85UV SR HPR (UVCL-Clear)	81	9	10	89	9	9	1.03	0.97	99.9	0.83	0.84	16	1.06	3	0	1